

| | |
|----------------------------|--|
| <i>Product SKU</i> | LNGD318 |
| <i>Thickness</i> | 3mm |
| <i>Length</i> | 1532mm |
| <i>Width</i> | 236.6mm |
| <i>Wear layer</i> | 0.7mm |
| <i>Colour</i> | Light Natural Oak |
| <i>Edge profile</i> | Micro Bevel |
| <i>UFH max temp.</i> | 27°C |
| <i>Pack weight</i> | 20.6kg |
| <i>Pack size</i> | 3.62m ² |
| <i>Warranty</i> | Domestic: Lifetime Commercial: 15 years |
| <i>Installation method</i> | Glued Down |



| Test Item | Testing Method | Testing Result |
|-----------------------------|-----------------------|---|
| Surface treatment: | - | Urethane ceramic bead/Excimer coating |
| Performance classification: | ISO10582 | 33: Commercial heavy 23: Domestic heavy |
| Dimensional stability: | ISO 23999 ASTM F 2199 | ≤0.2% |
| Heat curl: | ISO 23999 | ≤2mm |
| Static load: | ISO 24343-1 | ≤0.13 mm |
| Resistance to impact: | ISO 24344 | No crack |
| Residual indentation: | ISO 24343-1 | ≤0.05mm |
| Abrasion resistance: | EN 660-2 | Group T Pass |
| Light fastness: | ISO 105-B02 | ≥6 |
| Reaction to fire: | ISO9239-1 | Bfl -S1 |
| Resistance to staining: | ISO 26987:2008 | Pass |
| Slip resistance: | EN 13893 DIN 51130 | Class DS R10 |
| Chemical resistance: | ISO4918 | Pass. No more than a slight change in surface dulling, surface attack or staining |
| Castor chair test: | ISO 4918:2016 | Pass No visible damage after 25000 cycles |
| VOC emission: | FloorScore | Certified |
| | TUV PROFICERT | Certified |
| Environment: | EPD | Certified |